

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
14 July 2005 (14.07.2005)

PCT

(10) International Publication Number
WO 2005/063638 A1

(51) International Patent Classification⁷: **C03B 37/014**

(21) International Application Number:
PCT/EP2003/051102

(22) International Filing Date:
24 December 2003 (24.12.2003)

(25) Filing Language: English

(26) Publication Language: English

(71) Applicant (for all designated States except US): **PIRELLI & C. S.P.A.** [IT/IT]; Via Gaetano Negri, 10, I-20123 MILAN (IT).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **ADIGRAT, Antonio** [IT/IT]; Via Giardini, 1, I-85032 TEANA (PZ) (IT). **GRIECO, Stefano** [IT/IT]; Via Serroni, 11, I-84095

GIFFONI VALLEPIANA (SA) (IT). **CARONNA, Valeria** [IT/IT]; Via A. Maiuri, 33, I-84132 SALERNO (IT). **FERRI, Giuseppe** [IT/IT]; Via Bassi, 7, I-84013 CAVA DE' TIRRENI (SA) (IT). **COCCHINI, Franco** [IT/IT]; Via Mercanti, 150, I-84121 SALERNO (IT).


(74) Agents: **COLOMBO, Stefano Paolo** et al.; **MARCHI & PARTNERS S.r.l.**, Via Pirelli, 19, I-20124 MILAN (IT).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (BW, GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),

[Continued on next page]

(54) Title: PROCESS FOR PRODUCING A LOW-ATTENUATION OPTICAL FIBER



(57) Abstract: A process for producing a low-attenuation optical fiber comprises producing a soot core preform (23) by chemical deposition on a substrate; removing the substrate from the soot core preform (23), thereby forming a central hole (26) along the soot preform (23); drying and consolidating the soot core preform (23) in a consolidation furnace (20) to form a glass core preform (23); heating the glass preform (23) in the consolidation furnace (20) over a glass melting temperature to produce a reduction of the diameter of the central hole (26); and stretching the glass core preform (23) to completely close the central hole.

WO 2005/063638 A1



European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

Published:

— *with international search report*